



EKOTEKS

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar
İstanbul/ TÜRKİYE



Test
TS EN ISO/IEC 17025
AB-0583-T

TEST REPORT
DENEY RAPORU

AB-0583-T
20013326
04-20

Customer name: ARITEKS BOYACILIK TİCARET VE SAN. A.Ş.
Address: Hacı Şeremet 4. Sok. 59850 YULAFLI/ ÇORLU/ TEKİRDAĞ
Buyer name: -
Contact Person: ÖZGÜR KUŞKU
Order No: -
Article No: Arwowear T0 soft – 5920
Name and identity of test item: One sample of blue woven panel.
The date of receipt of test item: 20.04.2020
Re-submitted/re-confirmation date: -
Date of test: 20.04.2020-27.04.2020
Remarks: -
Sampling: The results given in this report belong to the received sample by vendor.
End-Use: -
Care Label: Not specified.

Number of pages of the report: 4

The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.

EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.

Seal **Date** **Customer Representative** **Head of Testing Laboratory**
 27.04.2020 Özlem ULUS Sevim A. RAZAK

27.04.2020

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T
20013326
04-20

REQUIRED TESTS	RESULT	COMMENTS
PHYSICAL PROPERTIES TESTS		
Pilling/ 125&500&1000&2000&5000&7000 revs	P	
P: Pass F: Fail R: Refer to retailer technologist. Requirements were given by vendor.		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a level of confidence of approximately 95 %. Tests marked (*) in this report are not included in the accreditation schedule.



This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T
20013326
04-20

TEST RESULTS

PILLING ; ISO 12945-2:2000

Martindale Test Machine with Lissajous Figure
Test was performed face to face.
Loading weight: 155 g±1
The average results are given for 2 samples, Number of observers: 2
Assessed with scale: K 3 Performed in the conditioned room (20±2°C-65%±4).
Original sample was tested as the client's request.

RESULT

4-5 @ 125 revs

REQUIREMENT

Min 4

Appearance change

-

PILLING ; ISO 12945-2:2000

Martindale Test Machine with Lissajous Figure
Test was performed face to face.
Loading weight: 155 g±1
The average results are given for 2 samples, Number of observers: 2
Assessed with scale: K 3 Performed in the conditioned room (20±2°C-65%±4).
Original sample was tested as the client's request.

RESULT

4-5 @ 500 revs

REQUIREMENT

Min 4

Appearance change

-

PILLING ; ISO 12945-2:2000

Martindale Test Machine with Lissajous Figure
Test was performed face to face.
Loading weight: 155 g±1
The average results are given for 2 samples, Number of observers: 2
Assessed with scale: K 3 Performed in the conditioned room (20±2°C-65%±4).
Original sample was tested as the client's request.

RESULT

4-5 @ 1.000 revs

REQUIREMENT

Min 4

Appearance change

-

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T
20013326
04-20

TEST RESULTS

PILLING ; ISO 12945-2:2000

Martindale Test Machine with Lissajous Figure

Test was performed face to face.

Loading weight: 155 g±1

The average results are given for 2 samples, Number of observers: 2

Assessed with scale: K 3 Performed in the conditioned room (20±2°C-65%±4).

Original sample was tested as the client's request.

RESULT

4 @ 2.000 revs

REQUIREMENT

Min 4

Appearance change

-

PILLING ; ISO 12945-2:2000

Martindale Test Machine with Lissajous Figure

Test was performed face to face.

Loading weight: 155 g±1

The average results are given for 2 samples, Number of observers: 2

Assessed with scale: K 3 Performed in the conditioned room (20±2°C-65%±4).

Original sample was tested as the client's request.

RESULT

4 @ 5.000 revs

REQUIREMENT

Min 4

Appearance change

-

PILLING ; ISO 12945-2:2000

Martindale Test Machine with Lissajous Figure

Test was performed face to face.

Loading weight: 155 g±1

The average results are given for 2 samples, Number of observers: 2

Assessed with scale: K 3 Performed in the conditioned room (20±2°C-65%±4).

Original sample was tested as the client's request.

RESULT

4 @ 7.000 revs

REQUIREMENT

Min 4

Appearance change

-

	PILLING RATING
5	No change
4	Slight surface fuzzing and/or pilling
3	Moderate surface fuzzing and/or pilling.
2	Distinct surface fuzzing and/or pilling.
1	Dense surface fuzzing and/or severe pilling