



**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**
Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar
İstanbul/ TÜRKİYE

TEST REPORT
DENEY RAPORU

17008195

03-17

EKOTEKS

Customer name: ARITEKS BOYACILIK TİCARET VE SAN. A.Ş.
Address: Velimeşe OSB Mah. Hacı Şeremet 5. Sokak 9/9 ERGENE/ TEKİRDAĞ
Buyer name: -
Contact Person: ÖZGÜR KUŞKU
Order No: -
Article No: -
Name and identity of test item: One sample of (claimed to be ;93%Metaaramid, 5% Paraaramid, 2% Carbon Twill Fabric 210 g/m² Navy)
The date of receipt of test item: 28.02.2017
Re-submitted/re-confirmation date: -
Date of test: 28.02.2017-02.03.2017
Remarks: -
Sampling: The results given in this report belong to the received sample by vendor.
End-Use: -
Care Label: Not specified.
Number of pages of the report: 3

Seal

Date
02.03.2017

Customer Representative
N. Fisun EROL

Head of Testing Laboratory
Sevim A. RAZAK

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

17008195

03-17

REQUIRED TESTS	RESULT	COMMENTS
COLOUR FASTNESS TESTS		
Colour Fastness to Non-Chlorine Bleach	-	
No requirement was given by vendor.		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a level of confidence of approximately 95 %. Tests marked (*) in this report are not included in the accreditation schedule.



This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

17008195

03-17

TEST RESULTS

COLOUR FASTNESS TO:

NON-CHLORINE BLEACH; TS 400 EN ISO 105 N02:1993(*)

Evaluated with ISO 105 A02 standard grey scale.

	<u>RESULT</u>	<u>REQUIREMENT</u>												
Colour Change	4	-												
Staining	<table border="1"><thead><tr><th>Acetate</th><th>Cotton</th><th>Nylon 6.6</th><th>Polyester</th><th>Acrylic</th><th>Wool</th></tr></thead><tbody><tr><td style="text-align: center;">3</td><td style="text-align: center;">3-4</td><td style="text-align: center;">2-3</td><td style="text-align: center;">3-4</td><td style="text-align: center;">3-4</td><td style="text-align: center;">3-4</td></tr></tbody></table>	Acetate	Cotton	Nylon 6.6	Polyester	Acrylic	Wool	3	3-4	2-3	3-4	3-4	3-4	-
Acetate	Cotton	Nylon 6.6	Polyester	Acrylic	Wool									
3	3-4	2-3	3-4	3-4	3-4									

COLOUR CHANGE	
5	Negligible or no change
4	Slightly changed
3	Noticeably changed
2	Considerably changed
1	Much changed

COLOUR FASTNESS RATING	
COLOUR CHANGE	
5	Negligible or no change
4	Slightly changed
3	Noticeably changed
2	Considerably changed
1	Much changed

COLOUR STAINING	
5	Negligible or no staining
4	Slightly stained
3	Noticeably stained
2	Considerably stained
1	Much stained

COLOUR STAINING	
5	Negligible or no staining
4	Slightly stained
3	Noticeably stained
2	Considerably stained
1	Much stained