



EKOTEKS

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar
İstanbul/ TÜRKİYE



Test
TS EN ISO/IEC 17025
AB-0583-T

**TEST REPORT
DENEY RAPORU**

AB-0583-T
20023017- ing
07-20

Customer name: ARITEKS BOYACILIK TİCARET VE SAN. A.Ş.
Address: Hacı Şeremet 5. Sok. 59850 YULAFLI/ ÇORLU/ TEKİRDAĞ
Buyer name: -
Contact Person: ÖZGÜR KUŞKU
Order No: -
Article No: Arox T2 WR/ Antic-5030
Name and identity of test item: One sample of white woven fabric.
The date of receipt of test item: 06.07.2020
Re-submitted/re-confirmation date: -
Date of test: 06.07.2020-09.07.2020
Remarks: -
Sampling: The results given in this report belong to the received sample by vendor.
End-Use: -
Care Label: Not specified.

Number of pages of the report: 3

The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.

EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.

Seal

Date
09.07.2020

Customer Representative
Özlem ULUS

Head of Testing Laboratory
Sevim A. RAZAK

09.07.2020

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T
20023017- ing
07-20

REQUIRED TESTS	RESULT	COMMENTS
ECOLOGICAL TESTS		
pH	-	
No requirement was given by vendor.		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a level of confidence of approximately 95 %. Tests marked (*) in this report are not included in the accreditation schedule.

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T
20023017- ing
07-20

TEST RESULTS

pH; ISO 3071:2005		
Place the sample and 100ml distilled water into flask and shake it mechanically for 2 hour. (± 5 min) Decant the extract, then the pH value of the aqueous extract of the textile is measured using pH meter at ambient temperature. (Distilled water's pH: 6.9 Temperature: $23.1^{\circ}\text{C} \pm 1$)		
	<u>RESULT</u>	<u>REQUIREMENT</u>
	7.4	-